

STAINLESS STEEL WIRE : CHEMICAL COMPOSITION

TYPE AISI	C Max%	Mn Max %	P Max %	S Max %	Si Max %	Cr :	Ni Mo	OTHER
302	0.12	2.0	0.045	0.030	1.0	17.0/19.0	8.0/10.0	
303	0.12	2.0	0.060	0.15/0.35	1.0	17.0/19.0	8.0/10.0	
304	0.07	2.0	0.045	0.030	1.0	17.0/19.0	8.0/11.0	
304 L	0.03	2.0	0.045	0.030	1.0	17.0/19.0	9.0/12.0	
308	0.08	2.00	0.025	0.020	0.50	19/21	9.5/11.0	
308 L	0.03	2.00	0.025	0.020	0.50	19/21	9.5/11.0	
309	0.08	2.00	0.020	0.015	0.50	19/21	9.5/11.0	
309 L	0.03	2.00	0.020	0.015	0.50	22/25	12/14.5	
310	0.15	2.00	0.015	0.015	0.60	25/28	20/22	
312	0.13	2.00	0.020	0.020	0.50	29/32	8.5/10	
316	0.08	2.00	0.020	0.020	0.50	18.0/20	11/14	2/3
316 L	0.03	2.00	0.020	0.020	0.50	18.0/20	11/14	2/3
321	0.08	2.00	0.045	0.030	1.0	17.0/19.0		